



# 3M™ Sun Control Window Film Neutral 70

- Metalised heat gain reduction technology
- Keeps occupants cool and comfortable
- Reduces heating and cooling costs
- Reduces glare and eye discomfort
- Extends the life and vibrancy in furniture, fittings and fabrics
- Reduces the risk of injury from flying glass




# 3M™ Sun Control Window Film Neutral 70

## Description

**3M Sun Control Window Films** are an elegant way to manage light and heat. 3M technology can significantly reduce heat gain and create a comfortable environment, especially in warmer months, as well as helping to reduce the workload of air conditioners and save energy costs. 3M Window Films also reduce glare and block almost the entire amount of UVA and UVB rays which are the main cause of fading and skin damage.

**3M's Neutral 70** is designed for use on the interior surface of windows. It's metalised technology reflects the sun's rays while allowing optical clarity to be maintained and rejects excess light to reduce glare.

## Solar Performance and light transmission



#### Features (on 6 mm clear glass)

Total Solar Energy Rejected 32% Glare reduction 22% UV rays blocked 98%

#### Film properties

Thickness 0.031mm / 31µm

Colour Neutral Material Polyester

Adhesive Pressure sensitive acrylic
Top coating Scratch resistant hard coat

#### Installation

3M Window Films are installed using a water and soap solution. Full adhesion is reached after approximately 20 days at 18°C (in dry conditions).

### Cleaning

3M Window Films may be cleaned 30 days after installation using ordinary window cleaning agents and avoiding the use of abrasive particles. Do not use rough sponges, cloths or brushes. Synthetic sponges, soft wipes or rubber squeegee cleaners are recommended.

Glass Type	Film Type on 6mm Glass	Visible Light Transmission	Visible Reflection Exterior	Visible Reflection Interior	Heat Gain Reduction	G-value (Solar Heat Gain Coefficient)	Total Solar Energy Rejected
Single Pane							
Clear	No film	89%	8%	9%	N/A	0.82	18%
	<b>Neutral 70</b>	<b>69%</b>	<b>9%</b>	<b>8%</b>	<b>17%</b>	<b>0.68</b>	<b>32%</b>
Tinted	No film	53%	6%	6%	N/A	0.63	37%
	<b>Neutral 70</b>	<b>42%</b>	<b>6%</b>	<b>7%</b>	13%	<b>0.55</b>	<b>45%</b>
Double Pane							
Clear	No film	79%	15%	15%	N/A	0.70	30%
	<b>Neutral 70</b>	<b>62%</b>	<b>16%</b>	<b>12%</b>	<b>8%</b>	<b>0.64</b>	<b>36%</b>
Tinted	No film	47%	8%	13%	N/A	0.51	49%
	<b>Neutral 70</b>	<b>37%</b>	<b>9%</b>	<b>11%</b>	<b>7</b> %	<b>0.47</b>	<b>53%</b>

The technical information, recommendations and other statements contained in this document are based upon European and/ or US tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond 3M's control and uniquely within the user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, the user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. The information provided in this report is believed to be reliable; however, due to the wide variety of intervening factors, 3M does not warrant that the results will necessarily be obtained. All issues regarding warranty and liability for the product and the effect of its use are governed in accordance with the provisions of the appropriate contract of sale unless local laws dictate otherwise.

