

Product Code	Series	Colour	Gauge	Construction
SF HP CH 50 PS	HP CHARCOAL 50	LIGHT CHARCOAL	50 μ (2Mil)	2PLY

Performance Fenestration Data

Visible Light Transmission	54%	Glare Reduction	50%
Visible Light Reflection (Internal)	6%	Solar Heat Gain Rejection	28%
Visible Light Reflection (External)	6%	Total Solar Energy Rejected	36%
Solar Energy Transmission	49%	Shading Coefficient	.75
Solar Energy Absorption	42%	Solar Heat Gain Coefficient (g value)	.64
Solar Energy Reflected	9%		
Ultraviolet Rejection	>99%	U-Factor	1.13
		Emissivity	.87

A patented superior scratch resistant coating is featured on all Solartek Window Films

High efficiency for the most demanding environments

For the most effective solar heat rejection in both commercial and residential applications, Solartek Window Films sets the industry standard

They're designed for challenging environments where a high level of solar control is needed – without compromising the appearance of the building

Key Features & Benefits	Solar Control Window Films
<p>Reduces Heat Gain – Reduces Energy Usage</p> <p>Reduces Eye Strain – Increases Comfort Levels</p> <p>Protects Against Fading – Blocks UV Rays</p> <p>Visual Enhancement – Improves Aesthetics</p>	<p>Suitable for application to windows, partition glazing, glazed exteriors, structural glazing, curtain walling, roof-lights and atrium glazing to effectively and economically reduce the problems associated with solar heat gain and visible glare. There are a variety of grades available offering different performances and colour choices to best meet your needs</p>

High Performance Low Sheen Window Films

One of the most popular solar heat rejecting films on the market providing effective solar energy rejection HP Charcoal 50 is an attractive and excellent choice providing unsurpassed solar performance together with high levels of visible glare reduction

Document No: HPCH50/1

T: 08000 15 18 15

Date: 2020

E: info@solartekfilms.com

www.solartekfilms.com